



# GYPSUM PLASTER K-G 691

Mortar for jointing plasterboards

**Areas of application:** Gypsum mortar for jointing plasterboards without reinforcing tape  
 Intended for jointing plasterboards with properly shaped edges without the use of reinforcing tape (reinforce non-factory, cut edges).  
 Can be also used for filling cavities and leveling out mineral groundworks on indoor surfaces

- Properties:**
- High grip
  - High resistance to cracking
  - Contains reinforcing fibers
  - High mechanic durability
  - Easy to process
  - Environmentally friendly

**Application procedure:**

Technical data		
Item no.	29143	29088
Packaging type		
Quantity per unit	5 kg	20 kg
Unit per pallet	200 Pcs/pallet	54 Pcs/pallet
Colour	White	
Consumption	1 kg/m <sup>2</sup> /mm	
Application time	≤ 60 min	
Compressive strength	≥ 3 MPa	
Layer thickness	≤ 3 mm	
Amount of water required	approx. 2.7 l/bag	approx. 10.8 l/bag
Reaction to fire	A1	
Adhesion to (Concrete)	≥ 0.25 MPa	

**The product conforms to:** • EN 13963

- Material base:**
- building plaster
  - Microfibers
  - Mineral fillers
  - Additives

**Surface:** Plasterboards mounted on a frame should be solid and stable  
 Adhesive-mounted plasterboards must be processed after the adhesive has dried completely.  
 Apply anti-corrosive coating on all metal elements that contact the plaster.

**Types of substrate:** **Gypsum plasterboards:** clean and possibly prime with GRUNTOLIT-SG 302  
**Concrete, reinforced concrete:** Prime with GRUNTOLIT-W 301 or EXPERT 6  
**Bricks and ceramic CMUs:** Prime with GRUNTOLIT-W 301 or EXPERT 6  
**Gipsputz:** Prime with GRUNTOLIT-SG 302 or EXPERT 5  
**Cement-lime plaster:** Prime with GRUNTOLIT-W 301 or EXPERT 6

**Preparation:** Pour the dry mix gradually to a container with a sufficient amount of clean, cool water, mixing manually or using a low-speed mixer to produce homogenous, lump-free mass. Leave to mature for 5 minutes, and then mix again.  
 If necessary, depending on the conditions, slightly adjust the amount of water added.  
 Do not mix the hardened grouting mixture again.



## GYPSUM PLASTER K-G 691

Mortar for jointing plasterboards

---

<b>Application procedure:</b>	Apply the mass to fill the joint or cavity completely, without leaving any empty spaces If necessary, apply in several layers after the previous one has dried After the layer has dried, grind with sandpaper or mesh, if necessary
<b>Application conditions:</b>	Apply in temperatures from +5 °C to +25 °C, these temperature refer to air, groundwork and product temperature.
<b>Storage:</b>	Up to 6 months from the date of manufacture, in dry areas and in non-damaged factory packaging.
<b>General information:</b>	This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.

---