



## AQUADUO 822

A two-component, polymer-cement waterproofing mortar.


### Areas of application:


Two-component polymer and cement hydroinsulation for making sealing coats on terraces, balconies and in bathrooms, kitchens, etc.  
 Also suitable for making water protecting underground insulations of building parts (cellars, foundations), resistance walls and concrete elements having contact with ground water as well as water basins and swimming pools.  
 Designed for waterproofing in rooms on such substrates as concrete, cement-lime plasters, gypsum substrates, screeds, also with floor heating and others.  
 The mortar is characterized by very high resistance to water, also under pressure, very large elasticity and capacity for bridging scratches and bed cracks with width of up to 0.75 mm. It is also a coating which protects concrete and reinforcement against corrosion caused by penetration of sulphates, chlorides and free carbon dioxide.

### Properties:

- Complete water-tightness
- High elasticity
- Waterproof
- Frost-resistant
- For terraces, swimming pools
- For insulation of foundations
- It requires no insert, reinforcing mesh
- UV-resistant

### Application procedure:



Technical data			
Item no.	36918	36996	37223
Packaging type			
Quantity per unit	10.7 kg	16 kg	32 kg
Unit per pallet	24 Pcs/pallet	24 Pcs/pallet	20 Pcs/pallet
Colour	Grey		
Consumption	1.5 kg/m <sup>2</sup> /mm		
Drying time	5 hours		
Application time	max. 60 min		
Layer thickness	2 - 4 mm		
Soluble chromium VI content	≤ 0.0002 %		
Possibilities to enter	24 hours		
Suitable for floor cover	3 days		
Adhesion to (Concrete)	≥ 0.5 MPa		
Adhesion to (Concrete)	≥ 0.5 MPa after exposure to water		
Adhesion to (Concrete)	≥ 0.5 MPa after freeze-thaw cycles		
Time of use approx.	≥ 60 min		
temperature resistance	-30 °C to +60 °C		
Waterproof quality	≥ 0,5 N/mm <sup>2</sup>		

The product conforms to: • EN 14891

### Material base:

- Quartz sand
- Mineral fillers
- Modifying additives
- Component B - polymer dispersion
- Portland cement



## AQUADUO 822

A two-component, polymer-cement waterproofing mortar.

<b>Surface:</b>	Concrete substrates must be at least 3 months old, while cement and cement-lime plasters and cement screeds must be at least 4 weeks old. Strongly absorbable and dusty substrates should be primed with GRUNTOLIT-W 301. When carrying out work during high temperatures, it is recommended to spray with water.
<b>Types of substrate:</b>	<p><b>Concrete, reinforced concrete:</b> moisten with water, if very absorbent, prime with GRUNTOLIT-W 301</p> <p><b>Cement plaster:</b> moisten with water, if very absorbent, prime with GRUNTOLIT-W 301</p> <p><b>Cement-lime plaster:</b> Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p><b>Cement screed:</b> moisten with water, if very absorbent, prime with GRUNTOLIT-W 301</p> <p><b>Autoclaved aerated concrete elements:</b> Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p><b>Bricks and ceramic CMUs, silicate:</b> Prime with GRUNTOLIT-W 301 or EXPERT 6</p> <p><b>Gypsum plasterboards:</b> Prime with GRUNTOLIT-SG 302 or EXPERT 5</p>
<b>Preparation:</b>	<p>The product is prepared in sets that facilitate mixing and dosing of individual ingredients. There are 2 types of sets available. 10.7 kg containing 2 bags of dry ingredient 4 kg each and a liquid ingredient in the amount of 2.7 kg, 16.0 kg containing 3 bags of dry ingredient 4 kg each and a liquid ingredient in the amount of 4.0 kg.</p> <p>Liquid component B must be poured to a tank and while pouring the dry component A keep stirring with a slow-speed drill with a mixer until homogenous mixture develops without lumps. Wait for 5-10 minutes and mix again.</p>
<b>Application procedure:</b>	<p>The prepared mortar should be applied to the sealed surface with a brush, roller or steel float in layers of thickness depending on the type of waterproofing performed.</p> <p>The second layer must be applied after reaching appropriate strength which allows to step on the applied coating and continue further works, however not earlier than after 4-5 hours. Thickness of each applied layer should not bigger than 2 mm. Thickness of insulation is dependent on its type: Insulation of light type - advisable thickness 2 mm - coverage 3 kg/m<sup>2</sup>, Insulation of medium type - advisable thickness 2.5 mm - coverage 3.7 kg/m<sup>2</sup>, Insulation of heavy type - advisable thickness 3.0 mm - coverage 4.5 kg/m<sup>2</sup>. Special attention should be paid to laying the insulation carefully in corners, edges and rounding. Ceramic tiles must be laid after 3 days using the elastic mortar.</p>
<b>Application conditions:</b>	<p>Apply at temperatures from +5 °C to +25 °C, these temperature refer to air, groundwork and product temperature. All groundwork surfaces must be load-bearing, tight, stable, even and clean and, if required, primed with GRUNTOLIT-W 301 or GRUNTOLIT-SG 302</p> <p>Scratches and cracks of bed more than 0.75 mm wide must be repaired by chiseling them and filling with the levelling grout 428 or another one adapted to the the type of bed. Special attention must be paid to preparation of edges (connections of walls and floors), in these places it is necessary to additionally set tapes and sealing corners or to round to the wall face (radius of min. 3 cm).</p>
<b>Instructions:</b>	Protect against precipitation, excessive sun rays, wind and frost during application and drying. Avoid contact with skin and protect eyes. Detailed guidelines are included in the material safety data sheet.
<b>Storage:</b>	The mortar can be stored for up to 12 months from production date in sealed packaging and at temperatures, ranging from +5 °C to +25 °C. The storage area shall be kept out of the reach of children, protected against direct sunlight and located far from heat sources and naked flames. It can be transported by any means of transport, at a temperature not lower than +5 °C. It is not subject to ADR provisions.



## AQUADUO 822

A two-component, polymer-cement waterproofing mortar.

---

### General information:

This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing. All technical data is given for the temperature of 20 degrees Celsius. These temperatures apply to air, bed and embedded material.